

Application No.: 10/761,548  
Docket No.: DW0085USNA

Page 2

**Amendment to Specification:**

On page 12, line 18, please replace the paragraph beginning "The results of these tests are shown in Table II." in its entirety with the following:

The results of these tests are shown in Table II. In the absence of mineral particulates, the presence of organic soaps in masterbatch compositions had little effect on extrudability (as measured by conditioning time) of films. In fact, masterbatches containing PPA-2 actually extruded slightly worse (longer conditioning time) when organic soap was present. The latter is shown by comparing the conditioning times of Sample 2 with Samples [[2, ]]4, 6 and 8.